



METHODS FOR CONSTRUCTING KIMONO-STYLE GARMENTS BASED ON UZBEK NATIONAL FABRICS

Ruzmatova Mokhichekhrakhon Dilshodbek kizi - First-year Master's Student

Fergana State Technical University

Email: infoversa25@gmail.com

Abstract *This article examines the methodological principles and construction techniques of kimono-style garments created using traditional Uzbek national fabrics. As global fashion increasingly assimilates cultural identities, the integration of national textiles such as atlas, adras, bekasam, and banoras into modern silhouettes has become highly relevant. The study explores how the structural properties, weaving technologies, and ornamental patterns of Uzbek fabrics influence garment construction and adaptation of the kimono form. The conceptual basis is supported by cultural fashion theory (Craik, 2009), textile science (Kadolph, 2014), and contemporary approaches to heritage-based design (Skov, 2011). Findings reveal that the natural drape, motif directionality, color symmetry, and fabric density play a decisive role in pattern-making, seam allowances, and fit adjustments. Practical recommendations are presented for modifying the traditional kimono structure to suit Uzbek textile geometry, preserving authenticity while ensuring ergonomic comfort and aesthetic harmony.*

Keywords: *kimono construction, Uzbek national fabrics, adras, atlas silk, heritage-based fashion, fabric structure, garment design, pattern-making, cultural identity, textile engineering.*

Introduction

The fusion of national cultural elements with contemporary apparel design has become a significant trend in global fashion. Traditional textiles are widely recognized not only for their aesthetic value but also for their cultural and historical significance. Uzbek national fabrics—such as *atlas* (ikat silk), *adras* (semi-silk ikat),

bekasam, and handwoven cotton-silk blends—represent centuries-old craftsmanship and rich symbolic meaning rooted in regional identity (Mumford, 2019). Their vibrant colors, ikat patterns, and unique weaving techniques provide exceptional opportunities for innovative garment construction.

In recent years, kimono-style garments have gained popularity in the European and Central Asian fashion markets due to their ergonomic comfort, minimalistic silhouette, and adaptable structure (Skov, 2011). The kimono's straight-cut geometry and modular design allow designers to reinterpret the form using diverse cultural fabrics while maintaining aesthetic appeal. However, adapting the kimono silhouette to the physical characteristics of Uzbek fabrics requires careful consideration of textile density, warp-weft balance, drape behavior, and motif alignment (Kadolph, 2014). Traditional Uzbek fabrics often feature elongated, vertically oriented motifs—*abr* (ikat) patterns—that significantly influence cutting direction, seam placement, and garment symmetry. Unlike the uniform surfaces of industrial fabrics, Uzbek textiles demand construction methods that preserve pattern continuity and cultural symbolism (Allison, 2020). This makes it essential to employ design methodologies that incorporate both textile engineering principles and artistic heritage. While studies on kimono construction are widely documented in Japanese garment engineering (Dalby, 2001), research focusing on the integration of Central Asian fabrics into kimono silhouettes is limited. Therefore, this article explores modern construction techniques tailored to the structural behavior of Uzbek national fabrics, emphasizing methodological adaptation, geometric analysis, and aesthetic preservation.

Methodology

This research employs a multidisciplinary methodology combining textile analysis, garment engineering, visual study, and comparative design approaches to determine effective construction techniques for kimono-style garments made from Uzbek national fabrics. The methodological framework is grounded in textile science (Kadolph, 2014), fashion theory (Craik, 2009), and heritage-based design

principles (Skov, 2011). A detailed examination of Uzbek national fabrics—*atlas*, *adras*, *bekasam*, *banoras*, and handwoven ikat varieties—was conducted to determine their physical and mechanical properties. The analysis focused on:

- fiber composition (silk, cotton-silk, cotton),
- density and weave structure,
- drape coefficient and pliability,
- warp–weft tension and stability,
- pattern directionality and motif repeat length.

Laboratory-based textile characterization methods described by Kadolph (2014) were used as the conceptual basis. Given that ikat patterns have strong vertical orientation and symbolic geometry, visual pattern alignment methods were applied. Fabric samples were laid flat, and:

- motif placement;
- symmetry axes;
- color transitions;
- directional lines;

were documented through photographic and schematic analysis. This approach follows heritage textile documentation methods described by Allison (2020).

Traditional Japanese kimono construction principles were reviewed and compared with the physical behavior of Uzbek fabrics. The comparative evaluation focused on:

- straight-block pattern drafting (Dalby, 2001);
- modular sleeve and collar construction;
- seam allowance distribution;
- traditional kimono measurements (kosode proportions).

This allowed identification of pattern elements requiring adaptation when applied to heavier or more structured Uzbek fabrics. Prototype patterns for kimono-style garments were developed using:

- classic kimono rectangles (body, sleeves, okumi panels);

- modified patterns with adjusted widths;
- variations that stabilize motif placement.

During prototyping, fabric samples were pinned and cut to observe real-time drape, seam tension, and alignment distortions. This practical stage followed garment engineering techniques outlined by Aldrich (2015). Several test garments (*muslin samples*) and partial prototypes (*half-scale forms*) were produced to evaluate:

- seam strength;
- fabric response to folding and edging;
- sleeve drop behavior;
- neckline shaping;
- overall silhouette balance.

Fit assessments were conducted on adjustable dress forms to examine how Uzbek fabrics behave in kimono-style silhouettes compared to silk crepe or cotton broadcloth commonly used in Japanese kimono construction (Skov, 2011). Semi-structured interviews were held with Uzbek textile artisans, fashion designers, and pattern-making specialists. The interviews evaluated:

- traditional expectations for motif integrity;
- cultural symbolism in ikat patterns;
- challenges in mixing traditional textiles with modern shapes;
- practical considerations in sewing national fabrics.

These qualitative insights helped validate technical findings and integrate intangible cultural aspects into construction decisions. All collected data were synthesized through thematic coding. Key themes included:

- the relationship between motif direction and garment geometry;
- structural constraints of handwoven textiles;
- necessary adjustments to traditional kimono patterns;
- principles for preserving authenticity while ensuring ergonomic fit.

This synthesis formed the foundation for the practical recommendations presented in later sections.

Results

The findings of this study reveal several significant outcomes regarding the construction of kimono-style garments using Uzbek national fabrics. The results highlight material-specific constraints, structural opportunities, and methodological considerations that distinguish Uzbek textiles from conventional kimono fabrics.

The textile analysis demonstrated that Uzbek ikat fabrics (*atlas*, *adras*, *bekasam*) have higher warp tension and more pronounced vertical motif alignment compared to Japanese kimono silks (Kadolph, 2014). The warp-faced structure and tightly bound ikat resist excessive draping, resulting in:

- reduced fluidity;
- stronger vertical fall lines;
- limited diagonal stretching.

These characteristics necessitate pattern adjustments to avoid fabric distortion, confirming earlier claims that traditional ikat demands adapted construction strategies (Allison, 2020). Visual analysis of pattern direction revealed that Uzbek ikat patterns typically rely on symmetrical, vertically elongated motifs (*abr* patterns). When placed on kimono blocks, motif misalignment occurred in:

- sleeve seams;
- okumi (front panel extensions);
- center-back seams.

This supports Skov's (2011) argument that culturally symbolic patterns require customized layout techniques. Adjusting the cutting layout—especially by widening the front panels and reducing sleeve width—improved motif continuity. Experimental prototyping showed that Uzbek fabrics create a more structured silhouette compared to the soft drape of Japanese *chirimen* silk (Dalby, 2001). As a result:

- sleeves maintained sharper edges,

- collars required interfacing for proper shaping,
- hem weights were necessary for balanced fall.

These results confirm that fabrics with higher density and minimal bias stretch require reinforced construction techniques to maintain visual harmony. Sewing trials revealed that handwoven ikat fabrics are prone to:

- fraying along the weft;
- weakening at needle entry points;
- pattern distortion under high seam tension.

To address these issues, reinforced French seams and double-fold bindings were found effective, supporting Aldrich's (2015) recommendations on handling delicate woven materials. When prototype garments were tested on dress forms, Uzbek fabrics produced a distinctive silhouette featuring:

- vertically elongated visual lines,
- slightly stiffened side seams,
- less pronounced shoulder drape.

While differing from the traditional kimono's fluid movement, this silhouette was perceived as aesthetically compatible with contemporary fashion. This aligns with Craik's (2009) observation that cultural reinterpretation can create new hybrid garment identities. Interviews with textile artisans and designers indicated that maintaining motif integrity was considered a primary requirement. Many noted that cutting through symbolic motifs diminishes the cultural authenticity of the garment. This qualitative insight reinforces the need for precise pattern placement and motif-preservation strategies (Mumford, 2019). The synthesis of experimental and analytical data resulted in a practical construction framework consisting of:

1. **Textile Evaluation** → identifying drape, density, motif repeat;
2. **Pattern Adaptation** → modifying kimono blocks to suit motif geometry;
3. **Cutting Optimization** → ensuring vertical motif alignment;
4. **Reinforced Construction** → using interfacing, reinforced seams;
5. **Fit Adjustment** → balancing structure with ergonomic comfort.

This framework supports heritage-based design methodologies discussed by Skov (2011) and contributes to modern garment engineering practices.

Discussion

The results of this study highlight the unique interaction between the structural properties of Uzbek national fabrics and the geometric characteristics of the kimono silhouette. These findings confirm that cultural textiles cannot be integrated into foreign garment forms without methodological adaptation, an assertion consistent with broader theories of cross-cultural fashion engineering (Craik, 2009; Skov, 2011). First, the study demonstrated that the warp-faced structure and high vertical motif intensity of Uzbek ikat fabrics create constraints not present in traditional Japanese kimono materials. While Japanese silks—such as *chirimen* and *habutae*—are characterized by fluid drape and uniform weave (Dalby, 2001), Uzbek *atlas*, *adras*, and *bekasam* show limited bias stretch and stronger structural rigidity (Kadolph, 2014). As a result, kimono patterns must be modified to prevent distortion of motifs and ensure ergonomic comfort. This supports Allison's (2020) findings that ikat pattern alignment directly influences garment construction strategies. Second, the role of motif preservation emerged as a central consideration during the design process. Because ikat patterns hold cultural symbolism and visually define garment identity, their misalignment disrupts both aesthetic balance and cultural authenticity. Artisan interviews reinforced this perspective, echoing Mumford's (2019) argument that cultural significance embedded in textile motifs must be respected in contemporary fashion applications. For this reason, widening front panels, adjusting sleeve proportions, and refining seam placements were necessary to preserve symbolic continuity. Third, the research showed that Uzbek fabrics create a more structured silhouette than the traditional kimono. This structured form—characterized by pronounced vertical lines and reduced fluidity—supports Craik's (2009) assertion that cultural reinterpretations naturally evolve into hybrid silhouettes. Rather than attempting to replicate the Japanese kimono precisely, designers must embrace the natural behavior of Uzbek textiles to produce garments

that are both culturally grounded and visually cohesive. Fourth, the need for reinforced construction methods—such as French seams, interfacing, and double-fold finishes—demonstrates that handwoven ikat fabrics respond differently to tension and movement. Aldrich (2015) notes that fabrics with high warp density require stabilized seam treatments, which aligns fully with the outcomes of this study. These reinforcements not only ensure structural integrity but also prolong garment durability, making the kimono-style design more suitable for contemporary fashion markets. Fifth, the results reveal that adapting kimono construction to Uzbek fabrics is not merely a technical exercise but an act of cultural translation. Each design decision—from cutting layout to shoulder shaping—carries cultural, symbolic, and aesthetic implications. This supports Skov's (2011) theory that heritage-based fashion design is inherently intercultural, requiring sensitivity to both originating and receiving cultures. Lastly, the construction framework developed in this study contributes a practical methodology for integrating national textiles into global garment forms. It bridges the gap between textile engineering and cultural fashion design and may serve as a foundational model for future research in heritage-based garment construction.

Overall, the discussion confirms that effective integration of Uzbek national fabrics into kimono-style garments requires a balance of cultural respect, technical precision, and aesthetic innovation. The findings underscore that successful heritage-based design is achieved not by imitation but by informed adaptation grounded in textile behavior and cultural meaning.

Conclusion

This study demonstrates that constructing kimono-style garments using Uzbek national fabrics requires a methodologically nuanced approach that accounts for the structural, aesthetic, and cultural characteristics of these traditional textiles. The findings confirm that Uzbek fabrics such as *atlas*, *adras*, *bekasam*, and *banoras* possess distinctive warp–weft dynamics, motif directionality, and drape behavior that differ significantly from the properties of traditional Japanese kimono silks

(Dalby, 2001; Kadolph, 2014). The research shows that successful adaptation of the kimono silhouette necessitates several critical modifications, including adjusted pattern geometry, reinforced seam techniques, and strategically optimized cutting layouts to preserve the integrity of ikat motifs. These adaptations ensure garment stability, motif continuity, and overall aesthetic harmony—considerations strongly emphasized in heritage-based fashion design (Skov, 2011; Allison, 2020). Moreover, incorporating Uzbek national fabrics into modern kimono-style garments contributes to cultural preservation and creative innovation within the contemporary fashion industry. Interviews with designers and artisans revealed that maintaining cultural symbolism in pattern placement is essential for authenticity and consumer appreciation. This underscores Mumford's (2019) assertion that national textiles carry cultural codes that should be respected in global fashion reinterpretations. The construction framework developed as a result of this research provides a practical methodological guide for designers, textile engineers, and educators. It establishes clear stages—textile evaluation, pattern adaptation, cutting optimization, reinforced construction, and fit assessment—that can be applied not only to kimono silhouettes but also to other cross-cultural garment forms.

In conclusion, the study affirms that integrating Uzbek national fabrics into kimono-style designs is both technically feasible and aesthetically enriching when approached with cultural sensitivity and engineering precision. This work contributes to the broader dialogue on heritage-based fashion innovation and offers valuable insights for future research in textile-informed garment construction, sustainable fashion design, and cultural garment hybridity.

References

- Aldrich, W. (2015). *Metric pattern cutting for women's wear* (6th ed.). Wiley.
- Allison, A. (2020). *Textile icons: Cultural meaning and structural design of ikat fabrics*. Bloomsbury Publishing.
- Craik, J. (2009). *Fashion: The key concepts*. Berg Publishers.
- Dalby, L. (2001). *Kimono: Fashioning culture*. Yale University Press.

Kadolph, S. J. (2014). *Textiles* (12th ed.). Pearson.

Mumford, D. (2019). *Silk, identity, and tradition in Central Asian textile art*. Routledge.

Skov, L. (2011). Fashion, the body and heritage: Cross-cultural garment translations. *Fashion Theory*, 15(4), 425–444.